



### ALU 70 XC

Alu 70 XC films are highly effective at reducing solar heat gain, whilst at the same time continuing to allow some natural light transmission. This film is providing effective protection against solar glare whilst its one-way mirror aspect guarantees privacy from prying eyes.



See the notice "new guarantees for the external films"



Fire-resistance rating  
**M1**



Storage from -5°C to +40°C  
**3 YEARS**



REACH RoHS compliant  
**RESPECTED**

### WIDTHS AVAILABLE:

↔ **152 cm**

### TECHNICAL DATASHEET


Data calculated based on film applied to clear glass 3 mm thick (\*on double glazing 4-16-4)

Ultraviolet transmission	1 %
Visible light transmission	43 %
Reflection of external visible light	40 %
Reflection of internal visible light	40 %
Total solar energy rejected	65 %
Total solar energy rejected 2*	69 %
Solar ratio :	
Solar energy reflection	44 %
Solar energy absorption	29 %
Solar energy transmission	27 %
Reduction in Solar Glare	67 %
g-value	0.36
u-value	
Shading coefficient	0.2
Installation type : Exterior	
Roll length	30,5 m
Film composition	PET
Thickness	75 μ

Colour from the outside : SILVER

### CONSTRUCTION

1. Hard scratch resistant layer, for durability and ease of maintenance during window cleaning
2. High optical quality polyester, with anti IR metal particles deposit
3. Bonding adhesive
4. High optical quality polyester
5. PS adhesive, glass polymerization within 15 days
6. Protection release liner, disposable after installation



### MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. 600-F0355 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

### INSTALLATION ADVICE

Vertical installation and on standard glass surface\*

Clear single pane	✓
Tinted single pane	✓
Reflective tinted single pane	✓
Clear double pane	✓
Tinted double pane	✓
Reflective tinted double pane	✓
Gas-filled double pane - Low E	✓
STADIP EXT. clear double pane	✓
STADIP INT. clear double pane	✓

✓ Yes    ! Caution    ✗ Not recommended

\*Recommendations provided on the basis of a glazed surface covering up to 2.5m<sup>2</sup>, contact us for definitive details or to obtain a thermal chock analysis report.